

FIREPRO CENTABUILD

HEAD OFFICE: AUCKLAND (09) 579 0367
 WELLINGTON (04) 568 7086 • CHRISTCHURCH (03) 379 9364
 www.firepro.co.nz sales@firepro.co.nz



Bradford™ Insulation

Fibermesh-650 Rockwool

Data Sheet

Product Description

Bradford Fibermesh-650 is an robust high density thermal insulation suitable for high temperature application. It consists of a flexible mat manufactured from a molten mixture of natural rock and recycled blast furnace waste stitched with wire to a facing of 25mm galvanised hexagonal wire mesh.

A suitable finish such as metal cladding is necessary to protect the insulation from weather and mechanical damage.

Applications

Process temperature control, energy conservation and personnel protection in the power generating, metallurgical, oil refining and chemical industries, including plant and equipment such as exhaust flues, hot gas ducts, boilers, furnaces, ovens, autoclaves and kilns.

Bradford Fibermesh-650 is easily installed by impaling the blankets on weld pins (with the mesh facing outwards) and securing with speed clips. The mesh joints may be laced together for extra strength if desired.

For safe handling instructions please refer to MSDS sheet.

Standard Size and Packaging

Thickness (mm)	Blanket Size (mm x mm)	Pieces/Pack
25	3600 x 750	2
38	3600 x 750	1
50	3600 x 750	1
63	3000 x 750	1
75	3000 x 750	1
88	2400 x 750	1
100	2400 x 750	1

Note: Not all of these standard sizes are held in stock. Some are subject to minimum order quantities.

Standard packaging is polythene bags.

Nominal weight per 25mm thickness 2.5kg/m² (excluding wire).


Maximum Service Temperature

Maximum service temperature is 650°C.

Thermal Conductivity

The thermal conductivity of Bradford Fibermesh-650 varies with the mean temperature of the insulation as shown in the graph. The curve is based on measurements made with a guarded hot-plate apparatus in accordance with BS 874 — 1973.

Authority: CSR Building Materials Research Laboratory.



Fibermesh-650 Rockwool

Fibermesh-650 Rockwool

Fire Resistance

When tested in accordance with AS 1530: Part 3 — 1976, Fibermesh-650 has the following Early Fire Hazard Indices:

Authority: CSR Building Materials Research Laboratory (NATA Certified).


Ignitability	0
Spread of Flame	0
Heat Evolved	0
Smoke Developed	0

Compression Resistance

Bradford Fibermesh-650 is designed particularly for flexibility. It does however have good compression resistant properties when subjected to normal compressive loads.

The graph shows the reduction in thickness of Fibermesh-650 under compressive load, measured in accordance with BS 2972 — 1975.

Authority: CSR Building Materials Research Laboratory.



Moisture Resistance

Exposure of Fibermesh-650 to a controlled atmosphere of 50°C and 95% relative humidity for 96 hours results in moisture absorption of less than 0.2% by volume.

Should the blankets become wet, full thermal efficiency will be restored on drying out.

Corrosion Resistance

Bradford Fibermesh-650 is faintly alkaline and is incapable of corroding steel. To maintain this condition, protection must be provided against contamination from external sources.

When tested in accordance with BS 3958: Part 5 — 1969, Fibermesh-650 has a pH of 7.5 — 9.0.

Fibermesh-650 contains less than 20ppm soluble chlorides which minimises the risk of external stress corrosion cracking in austenitic stainless steels. Stainless mesh may also be specially ordered for applications where galvanised mesh is not suitable.

Flexibility

Bradford Fibermesh-650 blankets are designed for maximum flexibility. They will essentially retain their thickness, while conforming to virtually any irregular shape.

Retention of the mat by the wire mesh prevents any cracking or breaking.

Vibration Resistance

Because Fibermesh-650 is stitched to wire mesh, the blankets are especially resistant to fallout under conditions where vibration is present.

Fibermesh-650 is particularly useful in situations involving both vibration and high temperatures where standard bonded insulation materials are less resistant to the effects of vibration.

Firepro Centabuild Ltd

8 Botha Road, Penrose, Auckland, Ph 09 5790367, Fax 09 5792511.

Unit 8b, 5 Western Hutt Road, Petone, Wellington, Ph 04 5687086, Fax 04 5860974.

23 Byron Street, Sydenham, Christchurch, Ph 03 3799364, Fax 033799380.